



GRINDING



NON-METALLIC MATERIALS Ceramics, geological applications



METALLIC MATERIALS Steels, light alloys



LEGEND

- Metallic or resin bond diamond discs for the levelling or grinding of very hard materials.
- SiC abrasive.
- Al₂O₃ abrasive, except P1000, P1200, P2400 and P4000.
- Resin bond diamond discs designed for hard metallic materials adapted to reduce process time.

STANDARDS AND EQUIVALENTS														
FEPA P	P 60	P 80	P 100	P 120	P 180	P 240	P 320	P 400	P 600	P 800	P 1000	P 1200	P 2400	P 4000
US	60	80	100	120	180	240	-	320	-	400	600	-	800	1200
µ average	260	200	150	120	76	60	46	35	26	22	18	15	10	5
I-MAX R	125			75			54			18				